

Metal Analysis on crumb rubber infill and playground rubber mulch

| Sample name | Cd (mg/kg) | Pb (mg/kg) | Zn (g/kg) |
|---|---------------|---------------|--------------|
| Crumb Rubber | | | |
| IMC Replay (R11) | 0.42 | 2.6 | 18.4 |
| LCC Canada (R5) | 0.73 | 33.1 | 14.1 |
| Surfacing Strategies (Black) (R7) | 0.65 | 23.6 | 14.8 |
| Genan (R10) | 1.12 | 20.5 | 22.2 |
| Entech (R15) | 0.66 | 11.1 | 22.1 |
| Rubber Mulch | | | |
| Rubberific (Brown) (R2) | 0.24 | 14.3 | 17.1 |
| Rubberific (Red) (R3) | 0.29 | 10.4 | 17.3 |
| Rubberific (Red) (Replicate 2) (R13) | 0.16 | 2.6 | 19.1 |
| Vigoro (Espresso Black) (R4) | 0.16 | 9.1 | 9.9 |
| Vigoro (Espresso Black) (Replicate 2) (R14) | 0.17 | 11.2 | 11.4 |
| Vigoro (Cedar Red) (R12) | 0.41 | 14.8 | 23.2 |
| New England Turf Store (Black) (R6) | 0.95 | 30.8 | 16.9 |
| Vigoro (Mocha Brown) (R8) | 0.32 | 5.9 | 8.8 |
| RubberScapes (R9) | 1.39 | 13.0 | 21.6 |